

Grade	Partikelgrößenverteilung			Durchschnittliche PG*	Schüttdichte [g/ml]	Feuchtigkeit** [%ww]
	D10 [µm]	D50 [µm]	D90 [µm]	[µm]		
ACCEL-101	NMT 30	40-60	NLT 80	50	0,26 - 0,32	3,0 - 5,0
ACCEL-102	NMT 45	70-100	NLT 140	90	0,27 - 0,33	3,0 - 5,0
ACCEL-102HD	NMT 45	70-100	NLT 140	90	0,30 - 0,36	3,0 - 5,0
ACCEL-103	NMT 30	40-60	NLT 80	50	0,26 - 0,31	1,0 - 3,0
ACCEL-105	./.	./.	NLT 38	./.	0,20 - 0,30	1,0 - 5,0
ACCEL-112	NMT 45	70-100	NLT 140	90	0,26 - 0,34	0,0 - 1,5
ACCEL-113	NMT 30	40-60	NLT 80	50	0,26 - 0,34	0,0 - 2,0
ACCEL-200	NMT 70	150-200	NLT 260	180	0,31 - 0,39	3,0 - 5,0
ACCEL-301	NMT 30	40-60	NLT 80	50	0,34 - 0,45	3,0 - 5,0
ACCEL-302	NMT 45	70-100	NLT 140	90	0,35 - 0,45	3,0 - 5,0

* PG = Partikelgröße, ** typische Werte, NMT = Not more than, NLT = Not less than