

Produkt	ASTM	N-326	N-330	N-339	N-347	N-375
Öl Adsorption (ml/100g)	D 2414	72	102	120	124	114
Iodzahl (mg/g)	D 1510	82	82	90	90	90
Asche (% max.)	D 1506	0,5	0,5	0,5	0,5	0,5
Siebrückstand 325 mesh (ppm max.)	D 1514	350	200	500	200	250
Stickstoffoberfläche (m²/g)	D 6556	78	82	90	85	93
Lieferform	-	Perlen	Perlen	Perlen	Perlen	Perlen