

Produkt	ASTM	HM-C521
Öl Adsorption (ml/100g)	D 2414	121
Iodzahl (mg/g)	D 1510	43
Asche (% max.)	D 1506	0,5
Siebrückstand 325 mesh (ppm max.)	D 1514	20
Stickstoffoberfläche (m²/g)	D 6556	40
Lieferform	-	Perlen