

<b>Emulsions- Styrol- Butadien- Kautschuk (ESBR)</b>	<b>Type</b>	<b>Styrolgehalt (%)</b>	<b>Mooney-Viscosität ML(1+4) @ 100°C</b>	<b>Ölgehalt phr</b>
Europrene®	1500	23.5	52	-
Europrene®	1502	23.5	52	-
Europrene®	1502 F	23.5	52	-
Europrene®	1509	23.5	35	-
Europrene®	1723	23.5	50	37,5 TDAE
Europrene®	1739	40	52	37,5 TDAE
Europrene®	1783	23.5	50	37,5 RAE
Europrene®	HS 630	63	56	-