

<b>Lösungs- Styrol- Butadien- Kautschuk (SSBR)</b>	<b>Type</b>	<b>Styrolgehalt (%)</b>	<b>Vinylgehalt (%)</b>	<b>Mooney-Viskosität ML(1+4) @100°C</b>	<b>Ölgehalt phr</b>
Europrene®	SOL B 1205	26		50	-
Europrene®	SOL R 72614	25	64	55	37.5 TDAE
Europrene®	SOL R C2525	26	24	54	-