

Copolymer	Gehalt Propylen (Gew-%)	Mooney-Viskosität ML (1+4) @125°C	Ölgehalt (Gew-%)
DUTRAL® CO 034	28	44	-
DUTRAL® CO 038	28	60	-
DUTRAL® CO 043	45	33	-
DUTRAL® CO 054	41	44	-
DUTRAL® CO 058	48	80	-