

| Product | Effective Density [g/cm ³] | Average Particle size [μm] | Particle Size [μm] (Malvern) | Pressure Resistance Isostatic [Psi] | Pressure Resistance Isostatic [Mpa] |
|-----------------------|--|----------------------------|------------------------------|-------------------------------------|-------------------------------------|
| Q-CEL® 300 | 0.21 | 90 | 5 - 200 | 500 | 3.4 |
| Q-CEL® 6014 | 0.14 | 85 | 5 - 200 | 250 | 1.7 |
| Q-CEL® 6019 | 0.19 | 75 | 5 - 175 | 500 | 3.4 |
| Q-CEL® 6019S | 0.19 | 70 | 5 - 150 | 500 | 3.4 |
| Q-CEL® 6020FPS | 0.2 | 45 | 5 - 90 | 500 | - |
| Q-CEL® 6717 | 0.19 | 52 | 5 - 105 | 500 | 3.4 |
| Q-CEL® 5028 | 0.25 | 75 | 5 - 120 | 750 | 5.2 |
| Q-CEL® 6028 | 0.28 | 70 | 5 - 150 | 750 | - |
| Q-CEL® 6036 | 0.36 | 60 | 5 - 125 | 1,000 | 6.8 |
| Q-CEL® 6042S | 0.42 | 50 | 5 - 90 | 2,000 | 13.8 |
| Q-CEL® 6048 | 0.48 | 50 | 5 - 100 | 3,000 | 20.7 |
| Q-CEL® 5070S | 0.7 | 35 | 10 - 100 | 3,500 | 24.2 |
| Q-CEL® 5019 | 0.19 | 72 | 5 - 150 | 500 | - |
| Q-CEL® 5032S | 0.32 | 63 | 5 - 150 | 1,000 | - |
| Q-CEL® 7019 | 0.19 | 80 | 5 - 150 | 500 | 3.4 |
| Q-CEL® 7023S | 0.23 | 85 | 5 - 120 | 750 | 5.2 |
| Q-CEL® 7028 | 0.27 | 75 | 5 - 120 | 1,000 | - |
| Q-CEL® 7036 | 0.36 | 63 | 5 - 125 | 1,000 | - |
| Q-CEL® 7040S | 0.4 | 54 | 5 - 100 | 2,000 | 13.8 |

The stated values correspond to typical values and hence do not represent a specification.